

Thermal Conductive Gap Fillers



TIF600G series offers excellent thermal performance and high compression set while remaining cost effective. This material conforms to surface irregularities under low application pressures to fill air gaps between components and the heat source.

TIF600G series combines good thermal conductivity of 6.2W/mK with high compressibility to produce low thermal resistance. TIF600G series is electrically non-conductivity, stable from -50°C to 200°C. The material is naturally tacky. Additional adhesive coating is not required.

◆ Features and Benefits

- 6.2W/mK thermal conductivity
- Highly compressible and cost effective
- Naturally tacky
- Electrically Isolating

◆ Typical Applications

- Cooling Components to the Chassis, Frame, or other type of heat spreader
- Mass Storage Drives
- Heat Pipe assemblies
- RDRAM Memory Modules
- Motor Control
- Telecommunication Hardware

Typical Properties of TIF600G series

Product Name	TIF600G	Test Method
Color	Garnet	Visual
Construction & Composition	Ceramic filled silicone elastomer	***
Thickness (inch/mm)	0.010 to 0.200 inch 0.254 to 5.08 mm	ASTM D751
Specific Gravity, (g/cc)	2.85	ASTM D297
Heat Capacity, (J/g-K)	1.0	ASTM C351
Hardness, (Shore A)	35	ASTM 2240
Tensile Strength, (psi)	55	ASTM D412
Continuous Use Temp, (°F/°C)	(-58 to 392°F) (-50 to 200°C)	***
Electrical		
Dielectric Breakdown Voltage, (VAC)	>2500	ASTM D149
Dielectric Constant, (1000 Hz)	4.5	ASTM D150
Volume Resistivity, (Ohm-meter)	3.1X10 ¹⁰	ASTM D257
Flame Rating	94 V0	equivalent UL
Thermal		
Thermal Conductivity, (W/m-K)	6.2	ASTM D5470

Canada:

3709 Pender St Burnaby B.C. Canada
TEL: +001-804-2998559
E-mail: sales@thermaziq.com

China:

Zhanghe Industrial District, Hengli Town,
Dongguan City, Guangdong Province, China
TEL: +86-769-83791280
E-mail: sales_dg@thermaziq.com

America:

113 Barksdale Professional Center
in the City of Newark, County of New Castle,
Zip code 19711, Delaware, USA

Taiwan:

1F No. 33-3, Nan-Shen Rd, Taipei City,
Taiwan, R.O.C.
TEL: +886-2-27838739
E-mail: sales_tw@thermaziq.com

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.